PROFIX

CP 390



Available colours



Plastic primer 1K

CP 390 primer is a single-component, ready-to-use product for priming plastic parts. It is an adhesion promoter which features insulating properties.

CP 390 primer is easy to apply and has a short drying time.

Note: The agent does not improve adhesion to PE polyethylene or PTFE teflon.

The product is available in 0.5 and 1-Litre tins.

PACKAGING	
Volume	Collective packaging
0.5 l	6 pcs.
11	6 pcs.



SHORT DRYING

TIME

READY TO USE



EASY APPLICATION





NO SANDING REQUIRED

EFFICIENT



SPRAY VISCOSITY

10-12 sek DIN Flow Cup 4mm



RECOMMENDED SIZES FOR PAINT STRAINER 190 µm



PAINT EFFICIENCY 10-12 m²/l



SHELF LIFE OF THE MIXTURE

Product ready for spraying



DRY FILM THICKNESS

1 coat - 10 μm



MINIMUM SHELF LIFE

CP 390: 24 months in originally sealed packaging



SUBSTRATE PREPARATION

The surface should be degreased, abraded (grey non-woven abrasive P1200), degreased again and washed with CP 011 water remover. Before application of CP 390, CP 012 antistatic remover needs to be applied



MIXING RATIO

Ready-to-spray product, does not need to be mixed with hardener or thinner



SPRAY GUN SETTINGS

Nozzle size: **1.2-1.4 mm**; Operating pressure: HVLP/RP **1.8-2.0 bar**



PROGRESS

APPLICATION

1-2 coats.

2-3 min evaporation time between coats



EVAPORATION TIME AFTER APPLICATION

20-30 min after coating at **20°C** and **65%** relative humidity